

Material Grade: DM4654 high property hard ferrite material

Property	Unit	Specification
Br Residual Flux Density	(mT)	460±10
	[Gs]	4600±100
Hcb Coercive Force	(kA/m)	344±12
	[Oe]	4300±150
Hcj Intrinsic Coercive Force	(kA/m)	432±12
	[Oe]	5400±150
(BH)max Max.Energy Product	(kJ/m ³)	41.6±1.6
	[MGOe]	5.2±0.2
μec Relative Permeability	/	1.05-1.1
Br temperature coefficient ΔBr/Br/ΔT	(%/°C)	-0.18
Hcj temperature coefficient ΔHcj/Hcj/ΔT	(%/°C)	0.10
Tc Curie Temperature	(°C)	460
ρ Density	(kg/m ³)	(4.90~5.10) ×10 ³
	[g/cm ³]	4.90~5.10
Anti-Bending Strength	(N/m ²)	(0.5~0.9) ×10 ⁸
	[kgf/mm ²]	5~9
Anti-Compressive Strength	(N/m ²)	≥6.9×10 ⁸
	[kgf/mm ²]	≥70
Anti-Tensile Strength	(N/m ²)	(0.2~0.5) ×10 ⁸
	[kgf/mm ²]	2~5

横店集团东磁股份有限公司 (DMEGC)

HENGDIAN GROUP DMEGC MAGNETICS CO., LTD.

